





Easy grip ECO Sponge 5/1

B385

BRAND, PRODUCT NUMBER AND NAME	BONUS	B385	ECO SPONGE 5/1
TARIC	3924900090		
PRODUCER/DISTRIBUTOR	Bonus Kft. 7800 Siklós, Ipartelepi út 2., Hungary +36 1 770 7000 info@bonus-hungary.com		
CERTIFICATES	MSZ EN ISO 9001:2015, MSZ EN ISO 14001:2015, MSZ 28001:2008		
STORAGE	Store in a dry, clean place. Keep away from fire and direct sunlight.		
PRODUCT PACKAGING	25um mirror-printed BOPP		
OUTER CASE	Recyclable, FC243-55 LDPE bag and foil		
COMPOSITION	20 kg/m ³ polyurethane foam with 30% plant based biopoliol component, 550g/m ² 100% recycled PET scourer with quartz		
TRADEMARK	Made in Hungary trademark and GREEN trademark issued by NGO Magyar Termék Nonprofit Kft. On 03.06.2013. Certificate number: 72/2013 / MTA		
PRESS KIT	https://img.bonus-hungary.com/products/B385/B385.zip		
WEBPAGE	https://en.bonuscleaningproducts.com/products/easy-grip-sponge-scourer-5x/		


LOGISTICS DETAILS	1×	1×			
	PIECE	PACKAGE	INNERCASE	OUTER CASE	PALETTE
		SALES UNIT		ORDER UNIT	
PIECES UNITS	1 PIECE	5 PIECE	20 PACKAGE	240 PACKAGE	1920 PACKAGE
NET WEIGHT GROSS WEIGHT	9 g	43 g 48 g	860 g 980 g	10,3 kg 12,0 kg	92 kg
DIMENSIONS 	9,5 × 7 × 4,5 cm	22 × 7 × 9,5 cm	38 × 36 × 23 cm	120 × 95 × 36 cm	120 × 80 × 230 cm
EAN-13	-	5997844301385	5997844300524	5997844300531	-

SPONGE COMPOSITION AND PROPERTIES	UNIT	TEST PROCEDURE	VALUE
NOMINAL FOAM DENSITY	kg/m ³	PN-EN ISO 845: 2000	20 – 23
NOMINAL HARDNESS CLD (40%)	kPa	PN-EN ISO 3386-1: 2000	3,65 - 4,50
RESISTANCE MINIMUM	%	PN-EN ISO 8307: 2000	3
COMPRESSION (50%) MAXIMUM	%	PN-EN ISO 1856: 2004	7
TENSILE STRENGTH MINIMUM	kPa	PN-EN ISO 1798: 2001	100
TENSION STRENGTH MINIMUM	%	PN-EN ISO 1798: 2001	150
COMPOSITION	Flexible polyether-polyurethane foam block made with Maxfoam or Novaflex® process. 30% plant based biopoliol.		

SCOURER LAYER INGREDIENTS	
COMPOSITION	100% RECYCLED POLYETHYLENE FIBERS
BINDING RESIN	VINYL-ACRYLIC RESIN
SCOURING MATERIAL	MINERAL GRAINS
COLORANTS	NATURAL – NON-TOXIC
USAGE	HOUSEHOLD
ADDITIVES	DOES NOT CONTAIN

SCOURER LAYER PROPERTIES	TOLERANCE	VALUE	UNIT
WEIGHT	± 5%	550	g/m ²
THICKNESS	± 1 mm	6,5	mm

SCOURER LAYER PERFORMANCE	TOLERANCE	VALUE	UNIT
TENSION STRENGTH Y DIRECTION	± 4%	115	N/cm ²
TENSION STRENGTH X DIRECTION	± 4%	130	N/cm ²
SCOURING EFFECT		≥270	mg

MADE BY	APPROVED
SÁGI NORBERT 2023.01.04. 	BOTOS ANDREJ 2023.01.04. 